



# APPLICATION GUIDE

## FAMILY OF PRODUCTS

FEATURES	PRODUCT																						
	RWB Patcher 1776	RWB 321 Old School Mix	RWB Smoother	RWB Strongcrete	RWB Strongcrete FD	RWB Strongcrete LST	RWB Rapid Anchor	RWB Flowtopper	RWB Flowsmooth	RWB Struccrete CI	RWB Swiftset	RWB Repairer	RWB Repairer F-1	RWB Repairer VOR, CI	RWB Seal Coat	RWB Freedom Grout	RWB Liberty Grout	RWB Patriot Grout	RWB Bonding Agent & Admix	RWB Acrylic Latex BAA	RWB Bonding Agent OTR	RWB Rapid Plug	
Aggregate Extendable for Deep Repair	●			●		●		●	●	●		●	●			●	●	●					
Yield, Ft <sup>3</sup>	Neat	.43	.43	.40	.43	.50	.43	.43	.43	.43	.43	.43	.43	.43	.43	.43	.43	.43	.43	NA	NA	NA	NA
	Extended	.56	NA	NA	.56	NA	.56	NA	.56	.56	.56	NA	.56	.56	NA	NA	.56	.56	.56	NA	NA	NA	NA
Lifts								●	●		●		●	●									
Min Thickness F = Feather Edge	F	F	F	1/2"	1"	1/2"	1"	F	F	1/2"	1/8"	1/2"	F	1/8"	F	1"	1"	1"	NA	NA	NA	NA	
Max Thickness	Neat	1"	1/8"	1/2"	3"	NA	3"	8"	1/2"	1"	3"	2"	3"	1"	2"	1/16"	3"	3"	3"	NA	NA	NA	NA
	Extended	4"	NA	NA	8"	8"	8"	NA	2"	2"	8"	NA	8"	4"	NA	NA	8"	8"	8"	NA	NA	NA	NA
Working Time	:60	:90	:50	:30	:12	:45	:10	:20	:30	:25	:24	:20	:30	:20	3:00	3:00	1:45	2:30	NA	NA	NA	NA	
Final Set	2:00	5:00	2:00	:55	:45	1:45	:20	1:30	1:30	1:45	:50	1:05	1:20	:45	5:00	6:00	5:30	5:30	NA	NA	NA	:05	
Temperatures	← MINIMUM 40°   MAXIMUM 90° →																						
Strengths (PSI)	5,000	4,000	2,000	7,000	6,500	6,000	5,000	5,400	3,000	9,000	6,000	7,000	4,500	5,500	3,500	6,000	7,000	7,500	NA	NA	NA	5,500	
Structural				●	●	●				●		●				●	●	●					
Cosmetic	●	●	●					●			●		●	●	●							●	
Walkways	●										●		●										
Garages	●			●	●	●						●	●										
Commercial Floor	●			●	●	●		●	●			●	●										
Industrial	●			●	●	●						●						●				●	
Horizontal Repair	●			●	●	●		●	●	●		●	●										
Traffic	●			●	●	●		●		●		●											
Vertical/Overhead		●	●			●				●	●			●	●							●	
Form and Pour						●				●													
Low Pressure Spray																			●	●	●		
Underlayment									●														
Self-leveling								●	●														
Cementitious	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●				●	
2-Component	●																						
Non-Sag Trowelable											●			●									
Self-Consolidation Pumpable						●				●						●	●	●					
Flowable	●			●	●	●	●	●	●	●		●	●			●	●	●					
Coating Acceptability		●	●												●								
Corrosion Inhibitor										●				●									
Shrinking Compensation																●	●	●					
Polymer Modified	●	●	●					●	●		●	●	●	●	●	●	●	●					
Light Color	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●				●	
Smooth Texture			●																				
Feather Edge Repairs	●	●	●					●	●				●		●								

Exclusively manufactured for JANELL, INC. by US SPEC



Distributed by JANELL, INC.

CINCINNATI, OH  
6130 Cornell Rd  
45242  
513-489-9111

DAYTON, OH  
801 E 1st St  
45402  
937-866-9111

NORWOOD, OH  
4686 Paddock Rd  
45229  
513-651-9111

COLUMBUS, OH  
831 Harmon Ave  
43223  
614-224-9111

ERLANGER, KY  
2930 Crescent Sprgs  
41018  
859-341-9111

LEXINGTON, KY  
970 New Circle Rd  
40511  
859-254-9111

